

## Technical Data Sheet

---

### Suave Polished Plaster - W Base | D Base

A durable synthetic resin based decorative plaster for interior surfaces.

**Product Characteristics:** Fine structure, impact and shock resistant, breathable, low VOC, excellent adhesion and easy to work with.

**Product Use:** Suave Polished Plaster is a decorative interior finish suitable for use on new and existing flat, clean and dry surfaces such as plasterboard, cementboard, concrete, blockwork, MDF and primed metal work. Texture can range from subtle to heavy, with a polish level from matte to gloss. Not suitable for wet areas. We recommend that you consult our technical adviser for special areas of application.

#### PROCESSING

---

**Application:** Mix Suave plaster well before use. After the Ambitec Primer coat has dried, apply the first coat of Suave plaster tightly and smoothly over the primer grit with a stainless steel plastering trowel. After drying, lightly wet the surface and apply a second coat with the desired texture and structure. When the plaster begins to dry, wet down and float. Once dry, sand to the desired gloss level. The right moment for sanding depends on temperature, humidity, etc. Sanding too quickly leads to chip strokes and excessive build-up. For optimal protection a final surface sealer can be applied to ensure Suave plaster is water and stain repellent and gives a unique richness to darker colours.

---

**Dilution:** If necessary, max 2% water.

---

**Coverage:** 2.25 kg/m<sup>2</sup>, 6.5 m<sup>2</sup> per 15 kg bucket at 1-1.5 mm thickness.

---

**Drying time:** Approximately 12hrs at 20°C, 65% rel. humidity. At a lower temperature and higher air humidity, allow longer drying times.

---

**Processing temp/  
Relative humidity:** Do not work at a substrate and ambient temperature of less than +5°C. Do not allow the relative humidity to exceed 80%.

---

**Cleaning:** Clean tools thoroughly with warm water immediately after use.

---

## SUBSTRATE PREPARATION

---

<b>General:</b>	The surface must be smooth and even, capable of supporting the plaster, completely set, clean, dry, and free of dust or grease. Sand and repair surface irregularities. Remove and/or repair all loose and unstable coats.
<b>New untreated substrates:</b>	Remove dust from the substrate. Coat with Ambitec Universal Primer. Min. 24 hours drying time. For concrete and block-work - the substrate must be coated in a leveling compound first.
<b>Existing, flaky/powdering substrates:</b>	Clean the substrate thoroughly and pre-treat powdery surfaces with a pigmented sealer. After drying, coat the substrate with Ambitec Universal Primer or Ambitec Renovation Primer. Min. 24 hours drying time.
<b>Existing dirty substrates:</b>	Remove and clean dirt from the substrate. Coat with Ambitec Universal Primer. Min. 24 hours drying time.
<b>Existing contaminated substrates:</b>	Pre-treat the contaminated substrate with a stain blocking primer. After drying, coat the substrate with Ambitec Universal Primer or Ambitec Renovation Primer. Min. 24 hours drying time.
<b>Existing with substrates lacquer/varnish:</b>	Clean and degrease the substrate. When dry, sand lightly, remove dust and coat the substrate with Ambitec Universal Primer or Ambitec Renovation Primer. Min. 24 hours drying time.
<b>Existing painted substrates:</b>	Clean the substrate thoroughly. After drying coat the substrate with Ambitec Universal Primer. Min. 24 hours drying time.
<b>Existing substrates with a decorative plaster:</b>	Remove dirt with a cleaner. Repair and/or smoothing should be done with an appropriate cement based product. When fully dry, coat with Ambitec Universal Primer or Ambitec Renovation Primer.
<b>Applicable to all substrates:</b>	If visible contaminants are still present in the substrate or leveling layer, it must always be pre-treated with Ambitec Renovation Primer to prevent bleed through in the top layer. Drying time at least 24 hours. PAY ATTENTION! When using pigmented decorative plaster products, the substrate must not contain any unbound lime particles (alkalinity). Important: Allow sufficient drying time between the various pre-treatments.

---

## ENVIRONMENTAL AND SAFETY

---

Avoid contact with eyes and mucous membranes. With induced risk (ceilings) wear safety goggles. If swallowed, do not induce vomiting – drink a small amount of water and seek medical attention. When skin contact occurs, wash with soap and water. Do NOT use solvents or thinners. If eye contact occurs, hold eyelids open and flush with clean, fresh water or a special eyewash solution and seek medical advice.

Do not allow to enter drains or watercourses. Contain and collect spillage with non-combustible absorbent materials, e.g., sand, earth and place in a suitable container for disposal according with the waste regulations.

For further information consult the Suave Material Safety Data Sheets.

---



## TECHNICAL DATA

---

Specific Mass:	Approx. 1.9 kg/L
Binding Agent:	Synthetic resin dispersion (styrene-acrylate copolymer)
Solid Components:	Approx. 60% v/v
VOC Content:	W Base 2 g/L   D Base <1 g/L
Colour:	White as standard. W Base for light colours. D Base for dark colours. To order based on a reference number or samples. Small colour variations may occur per shipment. These are caused by the mineral constituent parts. Buckets from different batches should always be mixed with each other prior to application.
Gloss Level:	Matte, satin and high gloss depending on finishing.
Texture Level:	Low, medium and heavy.
Packaging:	15 kg Plastic Bucket
Storage:	Transport and store in a frost-free environment. Keep packaging tightly closed at all times. Can be stored for approx. 8 Months after delivery date. Shelf life for at least 12 months. Opened packages have a limited shelf life.
Hazard classification:	See the Material Safety Data Sheet.

---

## GENERAL

---

A substrate and/or ambient temperature that is too low or a relative humidity that is too high and/or a moisture content of the substrate that is too high must be adjusted to the prescribed requirements. This can be done by means of heating, extracting moisture (dehumidifiers), ventilation, etc. It is necessary to continue these measures throughout the application and curing process.

The data in this publication is based on our current knowledge and experience. Due to the large number of possible influences in processing and application of our products, they do not indemnify the applicator from carrying out their own checks and tests. No guarantee of certain properties or the suitability of the product for a specific application can be derived from our data. All descriptions, drawings, photos, data, proportions, weights etc. provided herein are for general information purposes only; they may be subject to change without notice and do not constitute the contractually agreed quality of the products (product specification). Any property rights and existing laws and regulations must be observed by the recipient of our products at their own responsibility. Upon publication of this edition, all previous technical data sheets are invalid.

Version 21-10-2022

---

